

Ignitability of upholstered furniture according to EN 1021-1 and EN 1021-2

(1 appendix)

Introduction

RISE has by request of Elmo Sweden AB performed fire tests according to EN 1021-1 and EN 1021-2. The purpose of the tests is to form a basis for technical fire classification

Product

Leather called "ELMOSADDLE". According to the client the product consists of: Leather from European cattle, the product has a nominal thickness of 1.1 – 1.4 mm.

Sampling

The sample was delivered by the manufacturer. It is not known to RISE Safety – Fire Research if the product received is representative of the mean production characteristics.

The sample was received on May 23, 2019 at RISE Safety – Fire Research.

Test results

The upholstery combination was tested with cigarette (EN 1021-1) and match flame equivalent (EN 1021-2) as ignition sources.

The ignition sources were applied in a position along the junction between seat and back. Special care was taken to note any progressive smouldering or flaming combustion in the combination.

No progressive smouldering or flaming occurred within the 60 minute test time (non-ignition). The test results are given in appendix 1.

The test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of the test; they are not intended as a means of assessing the potential fire hazard of the materials or products in use.

Criteria

Section 3 in EN 1021-1, 2014 and EN 1021-2, 2014 describing "Criteria of ignition" with regards to "Progressive smouldering ignition" (3.1) and "Flaming ignition" (3.2).

RISE Research Institutes of Sweden AB

Postal address	Office location	Phone / Fax / E-mail
Box 857	Brinellgatan 4	+46 10 516 50 00
SE-501 15 BORÅS	SE-504 62 BORÅS	+46 33 13 55 02
Sweden		info@ri.se

This report may not be reproduced other than in full, except with the prior written approval of the issuing laboratory.

Assessment

The tested furniture upholstery combination called “ELMOSADDLE” meets the technical fire requirements according to EN 1021-1 and EN 1021-2.

Note

ELMOSADDLE were tested in combination with standard foam with a density of 22 kg/m³.

**RISE Research Institutes of Sweden AB
Safety - Fire Research Materials**

Performed by

Examined by

Henrik Fredriksson

Per Thureson

Appendix

1. Test results

Appendix 1

Test results - EN 1021-1, 2014 and EN 1021-2, 2014

Product

Lether called “ELMOSADDLE”. According to the client the product consists of: Leather from European cattle, the product has a nominal thickness of 1.1 – 1.4 mm.

Observations, EN 1021-1, ignition source cigarette

Table 1. Observations during the cigarette tests.

Test no	1	2
The cigarette was applied in a position along the junction between seat and back, min:s	00:00	00:00
Cover ignited, min:s	-*	-*
Filling ignited, min:s	-*	-*
The cigarette died out, min:s	35:38	41:03
Glow in the cover died out, min:s	-*	49:15
The test was finished, min:s	60:00	60:00

* Ignition/Flaming ignition of the materials was not observed.

Table 2. Test criteria and assessment, cigarette test.

	Test no	
	1	2
<i>Smouldering criteria</i>	Yes/No	
Unsafe escalating combustion (3.1 a)	No	No
Test assembly consumed (3.1 b)	No	No
Smoulders to extremities (3.1 c)	No	No
Smoulders through thickness (3.1 c)	No	No
Smoulders more than 1 h (3.1 d)	No	No
In final examination, presence of progressive smouldering (3.1 e)	No	No
<i>Flaming criteria</i>		
Occurrence of flames (3.2)	No	No

Appendix 1

Observations, EN 1021-2, ignition source small flame

Table 3. Observations during the match flame tests.

Test no	1	2	3
The ignition source was applied in a position along the junction between seat and back, min:s	00:00	00:00	00:00
Cover ignited, min:s	-*	-*	-*
Filling ignited, min:s	-*	-*	-*
The ignition source was removed, min:s	00:15	00:15	00:15
The test was finished, min:s	60:00	60:00	60:00

* Ignition/Flaming ignition of the materials was not observed.

Table 4. Test criteria and assessment, match flame test.

	Match flame equivalent		
	1	2	3
<i>"Smouldering criteria"</i>	Yes/No		
Unsafe escalating combustion (3.1 a)	No	No	No
Test assembly consumed (3.1 b)	No	No	No
Smoulders to extremities (3.1 c)	No	No	No
Smoulders through thickness (3.1 c)	No	No	No
Smoulders more than 1 h (3.1 d)	No	No	No
In the final examination, presence of active smouldering (3.1 e)	No	No	No
<i>"Flaming criteria"</i>			
Unsafe escalating combustion (3.2 a)	No	No	No
Test assembly consumed (3.2 b)	No	No	No
Flames to extremities (3.2 c)	No	No	No
Flames through thickness (3.1 c)	No	No	No
Flames longer than 120 s (3.2 d)	No	No	No

Appendix 1

Pre treatment

According to the client, the cover material has not been chemically treated to reduce ignitability. The cover material has therefore not been subjected to the water soaking and drying procedure described in Annex D before testing.

Conditioning

The tested product was conditioned for a minimum of 24 h at a temperature of (23 ± 2) °C and a relative humidity of (50 ± 5) %.

Date of test

June 3 and 5, 2019.